



# Vectra® E130i

Celanese Corporation - Liquid Crystal Polymer

Tuesday, April 9, 2019

## General Information

### Product Description

High temperature capability, easiest flow. Suitable where very thin walls are required. Used for broad range of SMT applications, with minimal dimensional change. 30% glass filled. Chemical abbreviation according to ISO 1043-1 : LCP Inherently flame retardant FDA compliant UL- Listing V-0 in natural and black at .2mm thickness per UL 94 flame testing. Relative-Temperature-Index (RTI) according to UL 746B: electrical 240°C, mechanical 240°C at 0.75mm. UL = Underwriters Laboratories (USA)

### General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Flame Retardant • Good Dimensional Stability • Good Flow • High Heat Resistance
Uses	• Thin-walled Parts
Agency Ratings	• FDA Unspecified Rating
RoHS Compliance	• Contact Manufacturer
Resin ID (ISO 1043)	• LCP

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.61	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.40	%	
Flow	0.10	%	
Water Absorption (Equilibrium, 73°F, 50% RH)	0.030	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2.18E+6	psi	ISO 527-2/1A
Tensile Stress (Break)	21800	psi	ISO 527-2/1A/5
Tensile Strain (Break)	1.6	%	ISO 527-2/1A/5
Flexural Modulus (73°F)	1.96E+6	psi	ISO 178
Flexural Stress (73°F)	31900	psi	ISO 178
Flexural Strain at Break	2.2	%	ISO 178
Compressive Modulus	2.03E+6	psi	ISO 604
Compressive Stress (1% Strain)	13500	psi	ISO 604
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	10	ft·lb/in <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	20	ft·lb/in <sup>2</sup>	ISO 179/1eU
Notched Izod Impact Strength (73°F)	9.5	ft·lb/in <sup>2</sup>	ISO 180/1A
Unnotched Izod Impact Strength (73°F)	15	ft·lb/in <sup>2</sup>	ISO 180/1U
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	71		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	529	°F	ISO 75-2/A
Heat Deflection Temperature (1160 psi, Unannealed)	421	°F	ISO 75-2/C
Vicat Softening Temperature	383	°F	ISO 306/B50

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

# Vectra® E130i

## Celanese Corporation - Liquid Crystal Polymer

Thermal	Nominal Value	Unit	Test Method
Melting Temperature <sup>2</sup>	635	°F	ISO 11357-3
CLTE - Flow	3.9E-6	in/in/°F	ISO 11359-2
CLTE - Transverse	1.1E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Electric Strength	810	V/mil	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	4.00		
1 MHz	3.30		
Dissipation Factor			IEC 60250
100 Hz	0.010		
1 MHz	0.025		
Arc Resistance	140	sec	Internal Method
Comparative Tracking Index	175	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Oxygen Index	45	%	ISO 4589-2

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	302 to 338	°F
Drying Time	4.0 to 6.0	hr
Suggested Max Moisture	0.010	%
Hopper Temperature	68 to 86	°F
Rear Temperature	599 to 617	°F
Middle Temperature	608 to 626	°F
Front Temperature	617 to 635	°F
Nozzle Temperature	635 to 653	°F
Processing (Melt) Temp	635 to 653	°F
Mold Temperature	176 to 248	°F
Injection Rate	Fast	
Back Pressure	< 435	psi

#### Injection Notes

Feeding zone temperature: 60 to 80°C  
 Zone4 temperature: 330 to 340°C  
 Hot runner temperature: 335 to 345°C

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 10°C/min